













Technical Data Sheet for: SOLACOAT CP (Porous) PRIMER: 2020

Description

Solacoat CP Primer is a water-based sealer, primer, undercoat designed to be used on exterior and interior porous surfaces for use under heat reflective coatings. The ceramic alloy component aids in the filling on uneven surfaces and optimizes for maximum heat reflectivity for temperature abatement.

Solacoat CP Primer can be recoated after 2 hours under good drying conditions. Do not apply when substrate temperature is below 15°C or when humidity is excessive.

Spreading rate is approximately 8-14 square metres per litre depending on application (brush, roller or spray), and the roughness of the substrate. Rough surfaces will have a spreading rate of around 8-10 square metres per litre and smooth surfaces will be around 8-14 square metres per litre.

Surface Preparation

All surfaces must be well prepared and free from dirt, oil, grease and other contaminants.

Brick/ Masonry/ Cement/ Concrete / Timber / PVC / Rubber / Asphalt type porous surfaces:

Fill any large holes with suitable filler following the manufacturer's directions. Remove all dust, grease and dirt by sweeping or suitable washing. Apply one coat of Solacoat CP Primer preferably using airless spray. On rough concrete surfaces it is advisable to back roll the wet paint with a long nap (20 mm) roller so as aid the coating of deep pits and holes in the substrate. It is not necessary to back roll the wet paint on smooth substrates.

Previously Painted Surfaces

Remove all loose and flaking paint with a wire brush or scraper. Ensure old paint has good adhesion to the substrate. Apply as per application above.

Application Method

Stir contents of can thoroughly with a wide flat stirrer ensuring the bottom of the can is reached. Apply 1 full coat of Solacoat CP Primer by airless spray using a 13 or 15 thou tip.

Brush/Roller

Pre-wet brushes and rollers. Flow paint generously and spread evenly – do not overspread. Use a quality bristle brush or a medium 12mm-nap roller on smooth surfaces for best results. On rough surfaces, use a 20mm-nap roller cover. Avoid excessive brushing or rolling.















SOLACOAT CP (Porous) PRIMER cont.

Spray

Suitable for application using standard airless spray equipment. If necessary, Solacoat CP Primer may be thinned sparingly with up to 100mls of water per litre of paint to help atomization.

Do not apply CP Primer Undercoat if substrate is below 15°C or is likely to fall below 15°C before the paint can dry.

Thinning

Not usually required, however it may be thinned sparingly with water.

Approximate Coverage

Covers approximately 8-10 square metres per litre on rough surfaces and approximately 8-14 square metres per litre on smooth surfaces.

Colours Available

Slight Grey in colour.

Drying Times

Approximate drying times at 25°C and 50% Relative Humidity.

Touch Dries: 30 minutes
Recoat: Minimum 2 hours.

Drying Times may be extended by adverse drying conditions or very high film build.

Cleanup

Clean all equipment promptly in water.

Properties

SOLIDS BY VOLUME: 40%

SOLIDS BY WEIGHT: 54%

WEIGHT PER LITRE: 1.4kg

GLOSS LEVEL: Low sheen

Resistance Properties

ABRASION: N/A HEAT: Up to 60°C

WEATHER: Interior/exterior use --- excellent when top coated.















SOLACOAT CP (Porous) PRIMER cont.

Additional Information

Designed to be used by professional applicators in an industrial environment.

END.